

BUILDING TRUST

SYSTEM DATA SHEET Sikafloor[®] MultiDur EB-27

SLIP RESISTANT BROADCAST COLOURED EPOXY FLOOR SYSTEM

PRODUCT DESCRIPTION

Sikafloor[®] MultiDur EB-27 is a 2-part epoxy coloured resin based flooring system that can provide a hard wearing, seamless, low maintenance, slip resistant finish when broadcast with different aggregate grades. For medium - heavy wear conditions. Thickness 2.0–4.0 mm. Internal use

USES

Sikafloor[®] MultiDur EB-27 may only be used by experienced professionals.

- On concrete and cementitious screeds with normal up to medium heavy wear e.g. storage and assembly halls, maintenance workshops, garages and loading ramps.
- On multi-storey and underground car park decks and for wet process areas, e.g. beverage and food industry

CHARACTERISTICS / ADVANTAGES

- Seamless
- High wear resistance
- Good chemical and mechanical resistance
- Easy application
- Waterproof
- Gloss finish
- Slip resistant
- Low maintenance

APPROVALS / STANDARDS

Fire classification test, Bfl-S1 according to DIN EN 13501-1.

System Data Sheet Sikafloor® MultiDur EB-27 February 2020, Version 01.02 02081190000000078

SYSTEM INFORMATION

System Structure

Sikafloor[®] MultiDur EB-27 system (~ 2–4 mm)

1 Primer		
Layer 1. Primer 2. Wearing finish 3. Seal /Top coat	Sikafloor [®] -150/-151	
	Sikafloor [®] -263 SL N or Sikafloor [®] - 264 N broadcast with quartz sand in excess	
	Sikafloor®-264 N	
Ероху		
Slip resistant, gloss finish		
Available in many colours		
~2.0– 4.0 mm		
	 2. Wearing finish 3. Seal /Top coat Epoxy Slip resistant, gloss finish Available in many colours 	

TECHNICAL INFORMATION

Reaction to Fire	BfI-S1 (DIN EN 13501-1)		
Chemical Resistance	Resistant to many chemicals. Contact Sika Technical Service for specific in- formation.		
Thermal Resistance	Exposure*	Dry heat	
	Permanent	+50 °C	
	Short-term max. 7 d	+80 °C	
	Short-term max. 12 h	+100 °C	
	Short-term moist/wet heat* u al (i.e. during steam cleaning *No simultaneous chemical a		
Skid / Slip Resistance	R11 V4 (Quartz Sand 0.3–0.8		
	R12 V6 (Quartz Sand 0.6–1.2	mm) (DIN 51130)	



APPLICATION INFORMATION

Consumption	Sikatioor® MultiDi	Sikafloor [®] MultiDur EB-27 system (~ 2–4mm)			
	Flooring System	Product	Consumption		
	Primer	1 × Sikafloor [®] -150 /-151			
	Wearing layer	Sikafloor [®] -263 SL N or	~ 4 kg /m² (2 kg/m²		
		Sikafloor [®] -264 N filled	binder + 2 kg/m ² quartz		
		1:1 with quartz sand	sand)		
		0.06–0.3mm			
	Sand broadcast	Quartz sand 0.3 – 0.8 mm	~ 4–6 kg/m²		
	Seal / Top coat	1–2 × Sikafloor [®] -264 N	~0.6–0.8 kg/m²		
Product Temperature	Please refer to the	Please refer to the individual Product Data Sheet			
Ambient Air Temperature	+10 °C min. / +30	+10 °C min. / +30 °C max.			
Relative Air Humidity	80 % r.h. max.	80 % r.h. max.			
Dew Point	Beware of conden		2°C above dow point to		
		The substrate and uncured floor must be at least 3 °C above dew point to reduce the risk of condensation or blooming on the floor finish.			
	+10 °C min. / +30 °C max.				
Substrate Temperature	+10 C mm. / +30	C max.			
	≤ 4% pbw				
	≤ 4% pbw	[®] -Tramex meter, CM - measure	ment or Oven-dry-meth-		
	≤ 4% pbw		ment or Oven-dry-meth-		
	≤ 4% pbw Test method: Sika od.				
Substrate Moisture Content	≤ 4% pbw Test method: Sika od. No rising moisture	[®] -Tramex meter, CM - measure e according to ASTM (Polyethyle	ne-sheet).		
Substrate Moisture Content	≤ 4% pbw Test method: Sika od. No rising moisture Before applying Si	[®] -Tramex meter, CM - measure e according to ASTM (Polyethyle ikafloor [®] -263 SL N/-264 Non Sika	ne-sheet). afloor®-150/-151 allow:		
Substrate Moisture Content	≤ 4% pbw Test method: Sika od. No rising moisture	[®] -Tramex meter, CM - measure e according to ASTM (Polyethyle ikafloor [®] -263 SL N/-264 Non Sika	ne-sheet). afloor®-150/-151 allow: Maximum		
Substrate Moisture Content	 ≤ 4% pbw Test method: Sika od. No rising moisture Before applying Si Substrate temperative 	[®] -Tramex meter, CM - measurer e according to ASTM (Polyethyle ikafloor [®] -263 SL N/-264 Non Sika ature <u>Minimum</u>	ne-sheet). afloor®-150/-151 allow: Maximum 3 days		
Substrate Moisture Content	 ≤ 4% pbw Test method: Sika od. No rising moisture Before applying Si Substrate tempera +10 °C 	[®] -Tramex meter, CM - measurer e according to ASTM (Polyethyle ikafloor [®] -263 SL N/-264 Non Sika ature <u>Minimum</u> 24 hours	ne-sheet). afloor®-150/-151 allow: Maximum		
Substrate Moisture Content	 ≤ 4% pbw Test method: Sika od. No rising moisture Before applying Si Substrate temperation of the second secon	[®] -Tramex meter, CM - measurer e according to ASTM (Polyethyle ikafloor [®] -263 SL N/-264 Non Sika ature <u>Minimum</u> 24 hours 12 hours 8 hours	ne-sheet). afloor®-150/-151 allow: Maximum 3 days 2 days 1 day		
Substrate Moisture Content	 ≤ 4% pbw Test method: Sika od. No rising moisture Before applying Si Substrate temperation of the second second	[®] -Tramex meter, CM - measured e according to ASTM (Polyethyle ikafloor [®] -263 SL N/-264 Non Sika ature <u>Minimum</u> 24 hours 12 hours 8 hours ikafloor [®] -264 N on Sikafloor [®] -26	ne-sheet). afloor®-150/-151 allow: Maximum 3 days 2 days 1 day		
Substrate Moisture Content	 ≤ 4% pbw Test method: Sika od. No rising moisture Before applying Si Substrate temperation of the second secon	 "-Tramex meter, CM - measured e according to ASTM (Polyethyle ikafloor"-263 SL N/-264 Non Sika ature <u>Minimum</u> 24 hours 12 hours 8 hours ikafloor"-264 N on Sikafloor"-26 ature <u>Minimum</u> 	ne-sheet). afloor®-150/-151 allow: <u>Maximum</u> <u>3 days</u> <u>2 days</u> <u>1 day</u> 3 SL N /-264 N allow: <u>Maximum</u>		
Substrate Moisture Content	 ≤ 4% pbw Test method: Sika od. No rising moisture Before applying Si Substrate temperation of the second secon	 "-Tramex meter, CM - measured e according to ASTM (Polyethyle ikafloor"-263 SL N/-264 Non Sika ature <u>Minimum</u> 24 hours 12 hours 8 hours ikafloor"-264 N on Sikafloor"-26 ature <u>Minimum</u> 30 hours 	ne-sheet). afloor®-150/-151 allow: <u>Maximum</u> <u>3 days</u> <u>2 days</u> <u>1 day</u> 53 SL N /-264 N allow: <u>Maximum</u> <u>48 hours</u>		
Substrate Moisture Content	 ≤ 4% pbw Test method: Sika od. No rising moisture Before applying Si Substrate temperation +10 °C +30 °C Before applying Si Substrate temperation +10 °C +10 °C +20 °C 	 "-Tramex meter, CM - measured e according to ASTM (Polyethyle ikafloor"-263 SL N/-264 Non Sika ature <u>Minimum</u> 24 hours 12 hours 8 hours ikafloor"-264 N on Sikafloor"-26 ature <u>Minimum</u> 	ne-sheet). afloor®-150/-151 allow: <u>Maximum</u> <u>3 days</u> <u>2 days</u> <u>1 day</u> 3 SL N /-264 N allow: <u>Maximum</u>		
Substrate Moisture Content	 ≤ 4% pbw Test method: Sika od. No rising moisture Before applying Si Substrate temperation of the second secon	 Tramex meter, CM - measured e according to ASTM (Polyethyle ikafloor®-263 SL N/-264 Non Sikature Minimum 24 hours 12 hours 8 hours ikafloor®-264 N on Sikafloor®-26 ature Minimum 30 hours 24 hours 16 hours 	ne-sheet). afloor®-150/-151 allow: <u>Maximum</u> <u>3 days</u> <u>2 days</u> <u>1 day</u> 53 SL N /-264 N allow: <u>Maximum</u> <u>48 hours</u> <u>30 hours</u> <u>24 hours</u>		
Substrate Moisture Content	 ≤ 4% pbw Test method: Sika od. No rising moisture Before applying Si Substrate temperation +10 °C +20 °C +30 °C Before applying Si Substrate temperation +10 °C +20 °C +30 °C Times are approxi 	 *-Tramex meter, CM - measurer e according to ASTM (Polyethyle ikafloor*-263 SL N/-264 Non Sika ature Minimum 24 hours 12 hours 8 hours ikafloor*-264 N on Sikafloor*-26 ature Minimum 30 hours 24 hours 	ne-sheet). afloor®-150/-151 allow: <u>Maximum</u> <u>3 days</u> <u>2 days</u> <u>1 day</u> 3 SL N /-264 N allow: <u>Maximum</u> <u>48 hours</u> <u>30 hours</u> <u>24 hours</u> anging ambient condi-		
Substrate Moisture Content Waiting Time / Overcoating	 ≤ 4% pbw Test method: Sika od. No rising moisture Before applying Si Substrate temperation +10 °C +20 °C +30 °C Before applying Si Substrate temperation +10 °C +20 °C +30 °C Times are approxitions particularly to the second s	 "-Tramex meter, CM - measured e according to ASTM (Polyethyle ikafloor"-263 SL N/-264 Non Sikafloor" 24 hours 24 hours 12 hours 8 hours 8 hours 16 hours 	ne-sheet). afloor®-150/-151 allow: <u>Maximum</u> <u>3 days</u> <u>2 days</u> <u>1 day</u> 3 SL N /-264 N allow: <u>Maximum</u> <u>48 hours</u> <u>30 hours</u> <u>24 hours</u> <u>24 hours</u> anging ambient condi- ity <u>Full cure</u>		
Substrate Moisture Content Waiting Time / Overcoating	 ≤ 4% pbw Test method: Sika od. No rising moisture Before applying Si Substrate temperation +10 °C +20 °C +30 °C Before applying Si Substrate temperation +10 °C +20 °C +30 °C Times are approxitions particularly to the second s	 "-Tramex meter, CM - measured e according to ASTM (Polyethyle ikafloor"-263 SL N/-264 Non Sikafloor"-264 Non Sikafloor 264 Non Sikafloor"-264 Non Sikafl	ne-sheet). afloor®-150/-151 allow: <u>Maximum</u> <u>3 days</u> <u>2 days</u> <u>1 day</u> 53 SL N /-264 N allow: <u>Maximum</u> <u>48 hours</u> <u>30 hours</u> <u>24 hours</u> <u>24 hours</u> anging ambient condi- ity <u>Full cure</u> <u>~ 10 days</u>		
Substrate Temperature Substrate Moisture Content Waiting Time / Overcoating Applied Product Ready for Use	 ≤ 4% pbw Test method: Sika od. No rising moisture Before applying Si Substrate temperation +10 °C +20 °C +30 °C Before applying Si Substrate temperation +10 °C +20 °C +30 °C Times are approxitions particularly to the second s	 "-Tramex meter, CM - measured e according to ASTM (Polyethyle ikafloor"-263 SL N/-264 Non Sikafloor" 24 hours 24 hours 12 hours 8 hours 8 hours 16 hours 	ne-sheet). afloor®-150/-151 allow: <u>Maximum</u> <u>3 days</u> <u>2 days</u> <u>1 day</u> 3 SL N /-264 N allow: <u>Maximum</u> <u>48 hours</u> <u>30 hours</u> <u>24 hours</u> <u>24 hours</u> anging ambient condi- ity <u>Full cure</u>		

PRODUCT INFORMATION

Packaging	Refer to the individual Product Data Sheet
Shelf Life	Refer to the individual Product Data Sheet
Storage Conditions	Refer to the individual Product Data Sheet

System Data Sheet Sikafloor® MultiDur EB-27 February 2020, Version 01.02 02081190000000078



BUILDING TRUST

MAINTENANCE

CLEANING

Refer to the Information Manual Sikafloor®- Cleaning Regime

FURTHER DOCUMENTS

Refer to :

- Sika[®] Information Manual Mixing & Applications of Flooring systems
- Sika[®] Information Manual Evaluation and Preparation of Surfaces for Flooring systems

LIMITATIONS

- Do not apply Sikafloor[®] MultiDur EB-27 on substrates with rising moisture.
- Freshly applied Sikafloor[®] MultiDur EB-27 must be protected from damp, condensation and water for at least 24 hours.
- The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking.
- For exact colour matching, ensure the Sikafloor[®]-264 N in each area is applied from the same control batch numbers.
- Under certain conditions, underfloor heating or high ambient temperatures combined with high point loading, may lead to indentations in the resin.
- If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO₂ and H₂O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.

VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA LIMITED Watchmead Welwyn Garden City Hertfordshire, AL7 1BQ Tel: 01707 394444 Web: www.sika.co.uk Twitter: @SikaLimited



System Data Sheet Sikafloor® MultiDur EB-27 February 2020, Version 01.02 02081190000000078 SikafloorMultiDurEB-27-en-GB-(02-2020)-1-2.pdf



BUILDING TRUST