

SYSTEM DATA SHEET

Sikafloor® MultiDur EB-14

BROADCAST UNICOLOUR EPOXY FLOOR COVERING

DESCRIPTION

Sikafloor® MultiDur EB-14 is a slip resistant, coloured, rigid flooring system based on epoxy resins

USES

Sikafloor® MultiDur EB-14 may only be used by experienced professionals.

- For concrete and cement screeds with normal up to medium heavy wear e.g. storage and assembly halls, maintenance workshops, garages and loading ramps.
- For multi-storey and underground car parks and for wet process areas, e.g. beverage and food industry

CHARACTERISTICS / ADVANTAGES


- Good chemical and mechanical resistance
- Easy application
- Liquid proof
- Gloss finish
- Easy cleanability

PRODUCT INFORMATION

Packaging	Please refer to the individual Product Data Sheet
Shelf Life	Please refer to the individual Product Data Sheet
Storage Conditions	Please refer to the individual Product Data Sheet

SYSTEM INFORMATION

System Structure



Sikafloor® MultiDur EB-14 system (~ 2–3 mm)

1. Scratch coat & broadcast	Sikafloor®-161 HC & broadcast with quartz sand 0.3–0.9 mm
2. Wearing coat	Sikafloor®-264 HC

Composition	Epoxy
Appearance	Slip resistant, gloss finish
Colour	Available in various colour shades.
Nominal Thickness	~2.0–3.0 mm

TECHNICAL INFORMATION

Chemical Resistance	Please refer to the chemical resistance chart of Sikafloor®-264 HC	
Temperature Resistance	Exposure*	Dry heat
	Permanent	+50 °C
	Short-term max. 7 d	+80 °C
	Short-term max. 12 h	+100 °C
Short-term moist/wet heat* up to +80 °C where exposure is only occasional (i.e. during steam cleaning etc.)		
*No simultaneous chemical and mechanical exposure.		

APPLICATION INFORMATION

Consumption	Sikafloor® MultiDur EB-14 system (~ 2–3 mm)		
	Coating System	Product	Consumption
	Scratch Coat	1 × Sikafloor®-161 HC filled at 1:0.5 with quartz sand 0.1–0.3 mm	~1.3 kg/m ²
	Broadcast in excess	Quartz sand 0.3–0.9 mm	~4–6 kg/m ²
	Top coat	2 × Sikafloor®-264 HC	~0.6–0.8 kg/m ²

Product Temperature	Please refer to the individual Product Data Sheet
---------------------	---

Ambient Air Temperature	+10 °C min. / +30 °C max.			
Relative Air Humidity	80 % r.h. max.			
Dew Point	Beware of condensation! The substrate and uncured floor must be at least 3 °C above dew point to reduce the risk of condensation or blooming on the floor finish.			
Substrate Temperature	+10 °C min. / +30 °C max.			
Substrate Moisture Content	When performing application work with Sikafloor® MultiDur EB-14, the substrate moisture content must not exceed 4 % pbw measured by Tramex. Test method: Sika®-Tramex meter, CM - measurement or Oven-dry-method. No rising moisture according to ASTM (Polyethylene-sheet).			
Waiting Time / Overcoating	Before applying Sikafloor®-264 HC on Sikafloor®-161 HC allow:			
	Substrate temperature	Minimum	Maximum	
	+10 °C	24 hours	3 days	
	+20 °C	12 hours	2 days	
	+30 °C	8 hours	1 day	
	Before applying Sikafloor®-264 HC on Sikafloor®-264 HC allow:			
	Title 1 Substrate temperature	Minimum	Maximum	
	+10 °C	30 hours	48 hours	
	+20 °C	24 hours	24 hours	
	+30 °C	16 hours	30 hours	
	Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity			
Applied Product Ready for Use	Temperature	Foot traffic	Light traffic	Full cure
	+10 °C	~ 72 hours	~ 6 days	~ 10 days
	+20 °C	~ 24 hours	~ 4 days	~ 7 days
	+30 °C	~ 18 hours	~ 2 days	~ 5 days

MAINTENANCE

CLEANING

Please refer to the Method Statement Sikafloor®-Cleaning Regime

FURTHER DOCUMENTS

- Sika® Method Statement Mixing & Applications of Flooring systems
- Sika® Method Statement Evaluation and Preparation of Surfaces for Flooring systems

IMPORTANT CONSIDERATIONS

- Do not apply Sikafloor® MultiDur EB-14 on substrates with rising moisture.
- Freshly applied Sikafloor® MultiDur EB-14 must be protected from damp, condensation and water for at least 24 hours.
- The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking.
- For exact colour matching, ensure the Sikafloor®-264 HC in each area is applied from the same control batch numbers.
- Under certain conditions, underfloor heating or high

ambient temperatures combined with high point loading, may lead to imprints in the resin.

- If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO₂ and H₂O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Kimia Sdn. Bhd.

Lot 689, Nilai Industrial Estate, 71800 Nilai
Negeri Sembilan D.K., Malaysia
Phone: +606-7991762
Fax: +606-7991980
e-mail: info@my.sika.com
Website: www.sika.com.my



SYSTEM DATA SHEET
Sikafloor® MultiDur EB-14
August 2017, Version 01.01
020811900000000055

SikafloorMultiDurEB-14-en-MY-(08-2017)-1-1.pdf